

Typical Physical Analysis

Sieve Size (mm)	Typical Gradation % Retained	Description
2 to 3.4	0	Fine Gravel
1 to 2	10	Very course sand
0.5 to 1	45	Course sand
0.25 to 0.5	29	Medium sand
0.15 to 0.25	11	Fine sand
0.05 to 0.15	3	Very fine sand
<0.05	2	Silt plus clay

This bunker sand meets USGA specifications tested by Tifton Physical Soil Testing Laboratory, Inc.

Other Analysis

Saturated hydraulic conductivity	1003.3 mm/hr
Penetrometer	3.5 kg/cm ²
Crusting potential	None
Grain shape	Sub-angular to sub-rounded
Calcium carbonate (calcaris)	None
Uniformity coefficient	3.4
Infiltration rate	129.1 cm/hr
Bulk density	1.46 g/cm ³